

Testreport surface resistant

Client Variér Furniture AS 6260 SKODJE		Product BLACK STAINED LACQUER ASH	
Client`s reference Jeanette Løining		Product description	
Date 03.03.2016		Revision nr./Revision date 0/	Date of receipt, tested object 22.02.2016
		R-no. R15695	Test completed date 02.03.2016

The samples are conditioned at 23° C and 50 % relative humidity for 1 week.

Test and method	Requirements	Test results	Pass/Fail
Cold liquid NS-EN 12720:2009+A1:2013		Scale 1-5 (5 is the best)	
Water 24 hours	≥4	4-5	Pass
Coffee (Nescafe Gold) 1 hour	≥4	5	Pass
Alcohol 48% 1 hour	≥4	4-5	Pass
Fat 24 hours	≥4	5	Pass
Dry heat NS-EN 12722:2009+A1:2013			
Dry heat 70° 20 min	≥4		
Dry heat 85° 20 min	≥4		

Comments:
Deviations from test standards:



Bård Vestre
 Manager

**Testreport surface resistant
Scratching**

Client Variér Furniture AS 6260 SKODJE		Product BLACK STAINED LACQUER ASH	
		Product description	
Client`s reference Jeanette Løining		R-no. R15695	
Date 03.03.2016	Revision nr./Revision date 0/	Date of receipt, tested object 22.02.2016	Test completed date 02.03.2016

The samples are conditioned at 23° C and 50 % relative humidity for 1 week.

Test and method	Requirements	Results	Pass/Fail
Scratching with fat in the surface, 24hours, 3N, NS 8058	≤0,5mm		
Scratching the surface, 3N, NS 8057	≤0,5mm	OK	Pass

Comments:
Deviations from test standards:



Bård Vestre
Manager

Testreport surface resistant

Client Variér Furniture AS 6260 SKODJE		Product NATURAL LACQUER ASH	
Client`s reference Jeanette Løining		Product description	
R-no. R15694		Date of receipt, tested object 22.02.2016	
Date 03.03.2016	Revision nr./Revision date 0/	Test completed date 02.03.2016	

The samples are conditioned at 23° C and 50 % relative humidity for 1 week.

Test and method	Requirements	Test results	Pass/Fail
Cold liquid NS-EN 12720:2009+A1:2013		Scale 1-5 (5 is the best)	
Water 24 hours	≥4	5	Pass
Coffee (Nescafe Gold) 1 hour	≥4	5	Pass
Alcohol 48% 1 hour	≥4	5	Pass
Fat 24 hours	≥4	5	Pass
Dry heat NS-EN 12722:2009+A1:2013			
Dry heat 70° 20 min	≥4		
Dry heat 85° 20 min	≥4		

Comments:
Deviations from test standards:



Bård Vestre
 Manager

**Testreport surface resistant
Scratching**

Client Variér Furniture AS 6260 SKODJE		Product NATURAL LACQUER ASH	
		Product description	
Client`s reference Jeanette Løining		R-no. R15694	
Date 03.03.2016	Revision nr./Revision date 0/	Date of receipt, tested object 22.02.2016	Test completed date 02.03.2016

The samples are conditioned at 23° C and 50 % relative humidity for 1 week.

Test and method	Requirements	Results	Pass/Fail
Scratching with fat in the surface, 24hours, 3N, NS 8058	≤0,5mm		
Scratching the surface, 3N, NS 8057	≤0,5mm	OK	Pass

Comments:

Deviations from test standards:



Bård Vestre
Manager

Test report Furniture



Client Variér Furniture AS 6260 SKODJE Norge		Product Variable Balans with Backrest	
Client's reference Jeanette Løining		Product specification - tested object	
Date 14.09.2015	Date of receipt, tested object 02.07.2015	R-no. R15523	Test completed date 11.09.2015
		Rev. no. / Rev. date 0/	



		Loading	To be tested	Result
Ref.	4. Safety requirements according to NS-EN 16139:2013			
4.1	Accessible corners are rounded or chamfered. The edges of the seat, back rest and arm rest are rounded or chamfered . All other are free from burrs and rounded or chamfered.		x	Passed
4.1	The edges of handles are rounded or chamfered.			
4.1	Ends of hollow components are closed or capped.			
4.1	Movable and adjustable parts shall be designed so that injuries and inadvertent operation are avoided.			
4.1	It shall not be possible for any load bearing part of the seating to come loose unintentionally		x	Passed
4.1	Lubricated parts shall be designed to protect users from lubricant stains.			
4.2	With the exception of tipping seats there shall be no shear and squeeze points created by parts of the seating operated by powered mechanisms, e.g. springs and gas lifts.		x	Passed
4.2	There shall be no shear and squeeze points created by forces applied during normal use as well as during normal movements and actions.		x	Passed

Test report Furniture

Stability according to NS-EN 1022:2005 Non swivelling chairs				
4.3	Forward	NS-EN 1022:2005 6.2	600N/20N	x Passed
4.3	Forward leg rest	NS-EN 1022:2005 6.3	600N/20N	
4.3	Sideways without arm rests	NS-EN 1022:2005 6.4	600N/20N	x Passed
4.3	Sideways with arm rests	NS-EN 1022:2005 6.5	250N/20N	
4.3	Backwards	NS-EN 1022:2005 6.6	600N/80N	x Passed
4.3	Backwards, variable geometry	NS-EN 1022:2005 7	1100N	x Passed
Stability according to NS-EN 1335-3:2009 Swivelling chairs				
4.3	Forward seat corner	NS-EN 1335-3:2009 7.1.1	270N	
4.3	Forward	NS-EN 1335-3:2009 7.1.2	600N/20N	
4.3	Forward leg rest	NS-EN 1335-3:2009 7.1.3	1100N/20N	
4.3	Sideways without arm rests	NS-EN 1335-3:2009 7.1.4	600N/20N	
4.3	Sideways with arm rests	NS-EN 1335-3:2009 7.1.5	250N/350N/20N	
4.3	Backwards, no adjustable back	NS-EN 1335-3:2009 7.1.6	600N/192N	
4.3	Backwards, adjustable back	NS-EN 1335-3:2009 7.1.7	1300N	
4.4 Rolling resistance of the unloaded chair NS-EN 1335-3:2009				
	Rolling resistance		≥12N	
	All castors are of the same type			
5. Strength and durability NS-EN 1728:2012				
6.4	Seat and back static load	1600N, 10 times, 560N, 10 times	x	Passed
6.5	Seat front edge static load	1300N, 10 times	x	Passed
6.6	Vertical static load on back	600N with 1300N in seat, 10 times	x	Passed
6.8, 6.9	Foot rest and leg rest static load	1300N, 10 times	x	Passed
6.10	Arm sideways static load	400N, 10 times		
6.11	Arm downwards static load	750N, 10 times		
6.13.1, 2	Vertical upwards static load on arm rests	Seat 250N, 10 times		
6.17	Seat and back durability test	Seat:1000N, Back: 300N, 100 000 cycles	x	Passed
6.18	Seat front edge durability test	800N, 50 000 cycles	x	Passed
6.20	Arm durability test	400N,30 000 cycles		
6.21	Foot rest durability test	1000N, 50 000 cycles	x	Passed

	Doc. nr. SK-73	 TEST 082
	Page : 3 of 3	
	Revision nr. : 3	
	Approved by : OAJ	
<h2>Test report Furniture</h2>		

6.15	Leg forward static load	500N with seat load 1000N, 10 times	x	Passed
6.16	Leg sideways static load	400N with seat load 1000N, 10 times	x	Passed
6.24	Seat impact test	Drop height 240 mm, 10 times	x	Passed
6.25	Back impact test	Height of fall 210 mm, 38°, 10 times	x	Passed
6.26	Arm impact test	Height of fall 210 mm, 38°, 10 times		
6.14	Auxilliary writing surface static load	300N, 10 times		
6.22	Auxilliary writing surface durability test	150N, 10 000 cycles		
7 Information for use				
7a - 7f	Requirements according to NS-EN 16139:2013		x	Passed

Safety, strength and durability requirements are fulfilled when:

- There are no fractures of any member, joint or component
- There are no losing of joints
- No major structural element is significantly deformed
- The chair fulfils its function after removal of the test loads

Deviation from the test standards:	
Comments:	
Summary	
The product is not approved according to the existing standards and requirements.	The product is approved according to the requirements for non domestic furniture, level 1 in NS-EN 16139:2013.
	X



Bård Vestre
Manager